










# Craig Wire Products Magnet Wire Cross Reference Guide

CWP Part Number	Thermal Class	Insulation Type	NEMA Standard (MW1000)	Application Type	
<b>CW Formvar</b>	105°C	Formvar	MW 15 (Round) MW 18 (Sq/Rect)	<ul style="list-style-type: none"> <li>• Oil Fill Transformers</li> <li>• Coils</li> <li>• Motors</li> </ul>	
<b>CW SPG/DPG</b> <i>Available over Enamel Unvarnished or Varnished</i>	155°C	Polyester Glass	MW 45 (Round) MW 46 (Sq/Rect)	<ul style="list-style-type: none"> <li>• AC/DC Motors</li> <li>• Generators</li> <li>• Field Coils</li> </ul>	
<b>CW MICA</b>	155°C	Mica tape		<ul style="list-style-type: none"> <li>• High Voltage Motors</li> <li>• Wind Machines</li> <li>• Transit Motors</li> </ul>	
<b>CW200<sup>UL</sup></b> <b>CW200Quad<sup>UL</sup></b> <b>CW200PLUS<sup>UL</sup></b>	200°C	Polyester with Amideimide Overcoat	MW 35-C (Round) MW 36-C (Sq/Rect)	<ul style="list-style-type: none"> <li>• AC/DC Motors</li> <li>• Generators</li> <li>• Hermetic Motors</li> <li>• Transformers</li> <li>• Electric Vehicles</li> </ul>	

 UL certified product



# Craig Wire Products Magnet Wire Cross Reference Guide

CWP Part Number	Thermal Class	Insulation Type	NEMA Standard (MW1000)	Application Type	
CW Nomex®	220°C	Aromatic Polyamide Paper	MW 60-C	<ul style="list-style-type: none"> <li>• Dry Type Transformers</li> <li>• Form Wound Coils</li> </ul>	
CW ML <sup>UL</sup> (HML, QML, SML)	240°C	Aromatic Polyimide Enamel	MW 16-C (Round) MW 20-C (Sq/Rect)	<ul style="list-style-type: none"> <li>• Aerospace</li> <li>• Traction Motors</li> <li>• Field Coils</li> <li>• Synchronous Motors</li> </ul>	
CW240TP	240°C	Aromatic Polyimide Tape	MW 65-C (Round) MW 64-C (Sq/Rect)	<ul style="list-style-type: none"> <li>• AC/DC Motors</li> <li>• Submersible Pumps</li> <li>• Aerospace</li> <li>• Traction Motors</li> <li>• Electric Vehicles</li> </ul>	

<sup>UL</sup> UL certified product